

Vandex BB75-Z

Surface applied, cement based render, waterproofing barrier for positive and negative water pressure applications

USES

Waterproofing of concrete and masonry structures both new and old. Vandex BB75-Z is a cementitious membrane and does not rely on crystal growth to achieve its waterproofing. As a result, BB75-Z can be used on most masonry surfaces, including sandstone, provided that the surfaces are adequately prepared.

Vandex BB75-Z has been formulated using sulphate resisting cement making it ideal for application in sewerage environments. It can be applied to either the pressure or non-pressure faces of the concrete or masonry.

Vandex BB75-Z is excellent for solving the problem of water seepage through concrete and masonry in both new and old structures.

Vandex BB75-Z is ideal in applications where the high pressure face is not easily accessible. It is also ideal for waterproofing the inside face of swimming pools, sewerage processing tanks, concrete block walls and any masonry surface where crystal growth waterproofing will not be effective due to a lack of alkalinity in the substrate.

Other applications include; basement walls, lift pits, water storage and drainage tanks, sewer aqueducts etc.

ADVANTAGES

- Abrasion resistant
- Applied to either the pressure or non-pressure face of concrete
- Approved for potable water contact
- Based on sulphate resisting cement making it suitable for use in sewerage processing tanks
- Works on masonry, brick, stone and concrete blocks where crystal growth treatments are not effective
- Non-toxic
- Suitable for permanent sunlight exposure after curing
- Tested to withstand a water head of 70 metres
- Colour compatible with the host concrete
- Can be applied to damp concrete

DESCRIPTION

Vandex BB75-Z is a ready-mixed, cementitious, surface applied, waterproofing membrane consisting of grey sulphate resistant cement, graded quartz sands and inorganic additives. Vandex BB75-Z is waterproof and has been tested to a pressure of 7.0 bar (70m water head). The initial and final bonding capability of BB75-Z is excellent, making it suitable for application to both vertical and horizontal surfaces. It is durable, resistant to frost and heat after setting and remains permeable to water vapour.

TEST REPORTS AND APPROVALS

OFFICIAL MATERIALS TESTING INSTITUTE CLAUSTHAL-ZELLERFIELD

- Mechanical properties
- Bend - tensile strength / compressive strength / adhesion / modulus of elasticity

LMP BAUSTOFFPRUFINSTITUT, BEINWLL AM BEE

- Resistance against sewage
- Shrinkage and swelling behaviour / bend tensile and compressive strength / structural composition



DESIGN CRITERIA

In most waterproofing applications, Vandex BB75-Z is applied in two coats by brush, trowel or spray. Specific minimum application rates are as follows;

Ground moisture - one coat by brush, trowel or spray at an application rate of 3.0 kg / m² / coat (total minimum layer thickness for one coat must be 1.5 mm).

Pressureless surface water - two coats by brush, trowel or spray at an application rate of 2.0 kg / m² / coat (total minimum layer thickness for two coats must be 2.0 mm).

Water under pressure - two coats by brush, trowel or spray at an application rate of 3 kg / m² / coat (total minimum layer thickness for two coats must be 3.0 mm).

Note: the maximum total thickness of all coats of the BB75-Z system should not exceed 5 mm.

PROPERTIES

Form:	Cementitious powder
Colour:	Cement grey
Bulk density:	1.30 - 1.50 kg/L
Compressive strength:	40 MPa after 28 days water storage
Bending tensile strength:	7 MPa after 28 days water storage
Elastic modulus:	2.16 x 10 ⁴ MPa after 28 days air cure at 23°C, 50% RH
Initial setting time:	2 - 4 hours
Full cure time at 20°C 50% RH:	5 days
Physical or chemical change:	Chemical cure
Application temperature:	5°C - 30°C
Service temperature (continuous ambient):	Minus 40°C - 120°C

CHEMICAL RESISTANCE

Vandex BB75-Z protects concrete against sewerage water, sea water, aggressive ground water and a range of chemical solutions. Vandex BB75-Z is approved for use in contact with potable water and is therefore suitable for the treatment of water storage tanks, reservoirs, water towers etc.

MAINTENANCE

No special requirements, any damage identified during normal inspections should be water blasted clean, repaired and recoated as appropriate.

SPECIFICATION CLAUSES

Where so designated on the drawings, surfaces to be waterproofed shall have a surface applied, cementitious waterproofing membrane installed. The waterproofing must form an impermeable layer on the surface of the substrate and must not rely on crystal growth within the substrate in order to be effective. It must have a proven capability of sustaining pressures of 7.0 bar (70 metre water head) while maintaining its waterproofing integrity. The waterproofing treatment must have a compressive strength greater than 35 MPa and bending tensile strength greater than 5 MPa after 28 days water cure. The cementitious waterproofing membrane must have a modulus of elasticity greater than 1.8 x 10⁴ MPa after 28 days cure. The setting time for the waterproofing must be in the range 2 - 4 hours and the bulk density for the dry powder before mixing must be in the range 1.30 - 1.50 kg/litre.

The cementitious waterproofing membrane must be non-toxic and be capable of being applied to concrete and masonry surfaces by trowel, or as a slurry by brush or by spray application through a hopper gun.

The waterproofing must be installed by a prequalified contractor nominated by the supplier and both the manufacturer and supplier must be accredited to ISO9001.

Vandex BB75-Z supplied by Parchem is such a product.

SURFACE PREPARATION

When applying Vandex BB75-Z to existing concrete or masonry, all surfaces to be waterproofed should be clean, sound and free of concrete curing compounds, form release agents, paints and all other coatings, dirt and contamination.

Concrete surfaces should be prepared by water blasting, grit blasting or wire brushing in order to remove the laitance and open the pore structure of the concrete in preparation to receive the Vandex BB75-Z.

Concrete surfaces should be free from major imperfections. All major imperfections must be repaired with a suitable cementitious reprofiling mortar such as Vandex Uni Mortar 1-Z which is suitable for reprofiling depths of 6 mm to 12 mm. Larger repairs may be carried out using multiple layers of Uni Mortar 1-Z or a suitable high build cementitious repair mortar.

PRIMING

Priming is not normally required on good quality concrete substrates, however all surfaces must be pre-watered before applying Vandex BB75-Z.

MOVEMENT JOINTS

All expansion and movement joints should be sealed with a suitable joint sealant after application of the Vandex BB75-Z. Consult your local Parchem sales office for advice on the joint sealing method best suited to your application.

CRACKS

All shrinkage and non-moving structural cracks having a width equal to or less than 0.3 mm will be waterproofed by applying Vandex BB75-Z directly bridging over the crack. Static cracks wider than 0.3 mm must be routed out to form a 'V' shaped groove with a hand or pneumatic chisel to a depth and width of approximately 25 mm. These larger cracks must be repaired by priming the chiselled out crack with two coats of Vandex Super, followed by the application of Vandex Uni Mortar 1-Z to fill the rebate flush with the concrete surface. All of the above products must be installed 'green on green', before the previous layer has dried out.

Live cracks cannot be waterproofed with Vandex BB75-Z. If the structure contains live cracks, Vandex BB75E-Z, an elasticised cementitious waterproofing membrane should be considered. Consult the local Parchem sales office for advice regarding the best method of waterproofing live cracks.

WATER SEEPAGE

All water seepage must be stopped using Vandex Plug prior to the application of Vandex BB75-Z. Do not attempt to apply BB75-Z over weeping or seeping substrates no matter how slow the seepage, as the BB75-Z will be damaged by the seepage water before it has a chance to cure.

APPLICATION INSTRUCTIONS

Vandex BB75-Z is supplied in the form of a dry powder and can be applied as a slurry by trowel, brush or spray.

To mix, place 25 kg of Vandex BB75-Z into a clean container and add 5 - 5.75 litres of clean tap water for brush or trowel application. Add 5.75 - 6.25 litres of water for spray application through a Vandex Hopper Gun.

The Vandex BB75-Z powder and water must be thoroughly mixed using a slow speed electric drill (300 rpm) or Festo type mixer fitted with a grout mixing paddle (PC 770163) for 3 minutes immediately prior to use. Mix only as much material as can be used in 20 minutes and stir the mixture frequently. If the mixture starts to set, do NOT add more water, simply stir the product to restore workability.

Ensure that all surfaces to which Vandex BB75-Z will be applied are pre-watered. The correct amount of pre-watering is measured by the substrate taking on a greenish appearance, however there must be no free surface water. A simple check can be performed by placing a hand on the pre-watered substrate and removing the hand. If the hand is wet from contact with the substrate, then the substrate is too wet and must be allowed time for the excess surface water to evaporate. Surfaces that have been pre-watered and dry out before application of the Vandex BB75-Z must be pre-watered again.

Apply the first coat from the base of the wall and work

towards the top using a trowel, a hopper gun or a plasterer's brush in a horizontal brushing action.

After 4 - 5 hours apply the second coat 'green on green' so that a chemical bond is achieved between the two coats. Do not apply more first coat during a day's work session than can be overcoated with a second coat during the same day.

When applying Vandex BB75-Z by spray using a Vandex Hopper Gun, ensure that the gun is held directly perpendicular to the surface at a distance of about 500 mm to ensure that the maximum impact energy is applied to the surface and to prevent any shadowing across small surface imperfections. After application of the first coat by spray, brush or trowel the wet surface to remove any entrapped air.

When applied by Hopper Gun, Vandex BB75-Z produces a very smooth 'orange peel' finish after application which may be too smooth for the bonding other coatings, tile mortars or finishes. If other products are to be applied over Vandex BB75-Z, roughen the surface slightly by brushing or brooming the surface of the BB75-Z while it is still wet, or alternatively, seed the Vandex surface with sand while it is still wet.

The cure time of Vandex BB75-Z is affected by both temperature and humidity. Humidity has an influence on waiting times between coats and resistance to rain. Ensure that the freshly applied BB75-Z is protected from rain for the first day, and the drying effects of the sun and wind during the first 5 days of cure.

In most waterproofing applications, Vandex BB75-Z is applied in two coats by brush, trowel or spray. Specific minimum application rates are as follows;

Ground moisture - one coat by brush, trowel or spray at an application rate of 3.0 kg / m² / coat. (Total minimum layer thickness for one coat must be 1.5 mm).

Pressureless surface water - two coats by brush, trowel or spray at an application rate of 2.0 kg / m² / coat. (Total minimum layer thickness for two coats must be 2.0 mm).

Water under pressure - two coats by brush, trowel or spray at an application rate of 3.0 kg / m² / coat. (Total minimum layer thickness for two coats must be 3.0 mm).

CURING AND PROTECTION

Surfaces treated with Vandex BB75-Z must be kept damp and must be protected from the drying action of direct sunlight for a minimum period of 5 days after application.

Protect all treated surfaces from wind and frost, by covering with plastic sheeting, damp hessian or equivalent.

CLEANING

Tools and equipment should be cleaned with water immediately after use.

LIMITATIONS

Vandex BB75-Z is suitable for use in open headed sewerage processing tanks. Consult Parchem for specific advise on the use of Vandex BB75-Z in closed sewerage environments where sulphuric acid concentrations may be high. In negative side applications, do not apply Vandex BB75-Z to substrates that are weeping. Use Vandex Plug to stop all water seepage before applying BB75-Z.

ESTIMATING

PACKAGING

Vandex BB75-Z: 25 kg bag

Vandex Uni Mortar 1-Z: 25 kg bag

Vandex Plug: 15 kg resealable plastic pail

COVERAGE

Vandex BB75-Z: 3.0 - 6.0 kg/m²
4 - 8 m² / 25 kg bag

Vandex Uni Mortar 1-Z: 6 - 12 kg/m²

STORAGE

12 months in original containers stored in cool, dry conditions i.e. not exceeding 30°C. Storage above this temperature may reduce storage life.

EQUIPMENT

Slurry application - Trowel, Plasterers brush - Vandex short handled brush or Vandex long handled brush.

Spray application - Vandex Hopper Gun, air compressor capable of 5 bar pressure and an air capacity of 500 litres/minute. Adjust the regulator at the compressor to 2.0 - 3.5 bar to achieve the desired spray finish.

ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

PARCHEM	CONCRETE REPAIR	FLOORING	JOINTING SYSTEMS	WATERPROOFING
TECHNICAL DATA SHEET	SEPTEMBER 07			
www.parchem.com.au	7 Lucca Road, Wyong NSW 2259	Sales 1800 624 322	Technical 1800 812 864	ABN 80 069 961 968 4